

WIRE TACKING, FIXTURING, AND RUGGEDIZATION Multi-Cure[®] 9-911 Rev. A

DESCRIPTION

Multi-Cure[®] Dymax 9-911 Rev. A is a high tensile strength material that is especially well suited for fast fixturing, structural wire tacking, and component ruggedization. Dymax 9-911 Rev. A has excellent adhesion to a wide variety of surfaces. It forms hard, smooth, translucent bonds to a variety of materials. Multi-Cure 9-911 Rev. A can be cured with either UV or visible light or activator. Shadowed adhesive can be cured with heat following UV or activator cure.

TYPICAL UNCURED PROPERTIES (not specifications)

Solvent Content	None - 100% reactive solids	
Chemical Class	Urethane (Meth)acrylate	
Appearance	Clear/Straw liquid	
Flash Point	>93°C (200°F)	
Solubility	Alcohols/Chlorinated Solvents/Ketones	
Toxicity	Low	
Viscosity (@20 rpm)	40,000 cP (nominal)	ASTM D-2556

TYPICAL CURED PROPERTIES (not specifications)

PHYSICAL

Durometer Hardness	D75	ASTM D-2240
Elongation at Break	26%	ASTM D-638
Tensile at Break	3,000 psi	ASTM D-638
Refractive Index	1.5	ASTM D-542
Water Absorption (24 hr)	1.4%	ASTM D-570

THERMAL

Coefficient of Linear Thermal Expansion	90×10^{-6} in/in/°C	ASTM D-696
Thermal Range (brittle/degrades)	-40° to +180°C (-40° to +350°F)	ASTM D-200

ELECTRICAL

Dielectric Strength	1,620 V/mil	ASTM D-1304
Volume Resistivity	$80 \times 10^{12} \Omega \cdot \text{cm}$	ASTM D-1304
Surface Resistivity	$230 \times 10^{12} \Omega$	ASTM D-1304
Dissipation Factor, 1 MHz	0.06	ASTM D-1304
Dielectric Constant, 1 MHz	4.1	ASTM D-1304

CURE DATA - Using 365 nm UV light^[1]:

	<u>Cure Time</u> (seconds)	<u>Intensity</u> ^[2] mW/cm ²	<u>Dymax Light-Welder</u> [®] <u>Lamp</u>
Fixture between glass slides	1	50	2000-EC
Ruggedization	5	150	5000-EC
Wire Tack	1	2000	3010-EC
Depth of cure (0.125 inch)	40	50	2000-EC

HEAT CURE DATA (secondary)

Heat may be used as a secondary cure for shadow areas, but only after product has been cured with UV or activator. The following is a guide and is dependent on the amount of material to be cured.

<u>Minimum Temperature</u>	<u>Time</u>
120°C (250°F)	30 minutes
150°C (300°F)	15 minutes

DISPENSING AND HANDLING ADHESIVE

Multi-Cure 9-911 Rev. A is available in syringes, cartridges, and bottles. It may be dispensed with a variety of automatic bench-top syringe applicators or other equipment as required. Direct questions relating to dispensing and curing systems for specific applications to the Dymax Tech Center at 860-482-1010.

Wear impervious gloves and/or barrier cream. Repeated or continuous skin contact with liquid adhesive will cause irritation and should be avoided. Do not wear absorbent gloves. Remove adhesive from skin with soap and water. Never use solvents to remove adhesive from skin or eyes.

STORAGE AND SHELF LIFE

Store material in a cool, dark place when not in use. Do not expose to UV light or sunlight. Material may polymerize upon prolonged exposure to ambient light. Replace lid immediately after use. Product has a one-year shelf life when stored below 90°F in the original, unopened container.

CAUTION

For industrial use only. Avoid breathing vapors. Avoid contact with eyes and clothing. In case of contact, immediately flush with water for at least 15 minutes; get medical attention. Wash clothing before reuse. Keep out of reach of children. Do not take internally. If swallowed, induce vomiting at once and call a physician. Repeated or continuous skin contact with liquid adhesive will cause irritation and should be avoided. For specific information, refer to the product Material Safety Data Sheet.

NOTES

[1] Lamps emitting high levels of shortwave light are not recommended. Less than 15% of the lamp's output should be 200-300 nanometer UV light.

[2] Nominal intensity measured at a predetermined distance. Listed intensity is not the maximum output of the lamp.

© 2003 Dymax Corporation

The data contained in this bulletin which represents typical results, is furnished for information only, and is believed to be reliable. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any product or method mentioned herein and to adopt such precautions as may be advisable for the protection of property and persons against any hazards that may be involved in the handling and use thereof. Nothing in this bulletin is to be interpreted as a representation of freedom from domination of patents owned by others or a license under a Dymax Corporation patent. We recommend that each prospective user test the proposed application before repetitive use, using the data as a guide. For specific information, refer to Material Safety Data Sheet before use.

Dymax Corporation - 51 Greenwood Road - Torrington, CT 06790 - Phone: 860-482-1010 - Fax: 860-496-0608
E-mail: info@dymax.com - www.dymax.com

Dymax Europe GmbH - Trakehner Strasse 3 - D-60487 Frankfurt am Main - Germany - Phone: (49) 69-7165-3568
Fax: (49) 69-7185-3830 - E-mail: dymaxinfo@dymax.de

Dymax[®], Light-Weld[®], Light-Welder[®], Multi-Cure[®], Ultra Light-Weld[®], *MEDI-CURE*[®] and MD[®] are trademarks of Dymax Corporation

